



association
for contract
textiles

ACT Voluntary Performance Guidelines for Knit Fabrics

ACT Voluntary Performance Guidelines for Flammability and four aspects of fabric durability—Wet & Dry Crocking, Colorfastness to Light, Physical Properties, and Abrasion—make fabric specification easier.

To give architects, designers, and end-users a vast amount of performance information in a succinct visual way, ACT developed icons to indicate that a fabric meets or exceeds guideline requirements. Look for these Registered Certification Marks on ACT Member Company sampling to assure that the fabrics you specify perform up to contract standards and pass all applicable testing.

All ACT Voluntary Performance Guidelines cover woven, coated and knit fabrics for indoor use. “Knit Fabrics” are made by interlocking loops of one or more yarns.

Test methods included in the Guidelines measure fabric performance under standard laboratory conditions and are intended to represent the most current test version. Note: Individual ACT Member product information may represent a different version of a test method depending on the date the product was introduced to market.

Important: These tests represent minimum requirements, which are subject to change without notice and may not reflect requirements or laws in all locations.

Flammability



The measurement of a fabric's performance when it is exposed to specific sources of ignition.

Note: ACT guidelines specify different flammability tests dictated by the intended end use for the fabric.

ACT GUIDELINES

Upholstery

California Technical Bulletin 117-2013 Section 1 – Pass

Direct Glue Wallcoverings and Adhered Panels

ASTM E84 (Adhered Mounting Method) – Class A or Class 1

Wrapped Wall Panels and Upholstered Walls

ASTM E84 (Unadhered Mounting Method) – Class A or Class 1

Panel System Furniture

Any one or combination of the following: UL recognized component under Office Panel Fabrics category, UL 1286 Listed, ASTM E84 (Adhered or Unadhered Mounting Method) – Class A or Class 1

Draperies

NFPA 701 Method 1 or 2 as appropriate – Pass



association
for contract
textiles

Wet & Dry Crocking



Transfer of dye from the surface of a dyed or printed fabric onto another surface by rubbing.

ACT GUIDELINES

Upholstery

AATCC 8 Dry Crocking, Grade 4 minimum
 Wet Crocking, Grade 3 minimum

Direct Glue Wallcoverings

AATCC 8 Dry Crocking, Grade 3 minimum
 Wet Crocking, Grade 3 minimum

Wrapped Panels and Upholstered Walls

AATCC 8 Dry Crocking, Grade 3 minimum
 Wet Crocking, Grade 3 minimum

Draperies


AATCC 8 (Solids) Dry Crocking, Grade 3 minimum
 Wet Crocking, Grade 3 minimum

AATCC 116 (Prints) Dry Crocking, Grade 3 minimum
 Wet Crocking, Grade 3 minimum



association
for contract
textiles

Colorfastness to Light



A material's degree of resistance to the fading effect of light.

ACT GUIDELINES

Upholstery

AATCC 16 Option 1 or 3

Grade 4 minimum at 40 hours*

Direct Glue Wallcoverings

AATCC 16 Option 1 or 3

Grade 4 minimum at 40 hours*

Wrapped Panels and Upholstered Walls

AATCC 16 Option 1 or 3

Grade 4 minimum at 40 hours*

Drapery

AATCC 16 Option 1 or 3

Grade 4 minimum at 60 hours*

**Note: There is no direct correlation between the numbers of testing hours and hours of service in the field.*

Physical Properties



Key factors in assessing overall durability of a fabric vary depending on the fabric construction.

ACT GUIDELINES

Upholstery

Pilling

ASTM D3511 (Brush Pill), Class 3 minimum Or ASTM D4970, (Martindale Tester), Class 3 minimum
Pilling is the formation of fuzzy balls of fiber on the surface of a fabric that remain attached to the fabric.

Aesthetic issues of pilling and fuzzing that sometimes occur on textile products do not impact the durability or functionality of the material. Laboratory testing provides some insight into the propensity for a textile to pill or fuzz; however, lab tests alone cannot predict field performance since they do not consider variables (e.g., care and maintenance, misuse, environment) encountered in the actual end-use application.

Breaking Strength

ASTM D5034 (Grab Test), 50 lbs. minimum both directions

Breaking Strength is the measurement of stress exerted to pull a fabric apart under tension.

Tear Strength

ASTM D2261 6.0 lbs. minimum both directions

Tear Strength is the measurement of stress exerted to rip the fabric under tension.

Snag Testing

ASTM D3939 (Mace Snag), Class 3 minimum

Snagging is the formation of yarn pulls on the surface of a fabric.

Stretch & Set

ACT has chosen not to establish a minimum requirement for this performance characteristic since the ability of a fabric to return to its initial state is strongly impacted by factors that are attributed to furniture construction and fabrication such as the density of foam. The SAE J855 test can be used to evaluate the stretch and set of a knit fabric; however, ACT suggests that you consult with both your fabric supplier and furniture manufacturer to determine if there are any potential issues.

Wrapped Panels and Upholstered Walls

Breaking Strength

ASTM D5034 (Grab Test), 35 lbs. minimum both directions

Abrasion




Low Traffic /
Private Spaces –
Knit Upholstery Fabrics

The surface wear of a fabric caused by friction.

ACT GUIDELINES

Low Traffic / Private Spaces – Knit Upholstery Fabrics

ASTM D4157 (ACT approved #10 Cotton Duck) 15,000 double rubs Wyzenbeek method
ASTM D4966 (12 KPa pressure) 20,000 cycles Martindale method



High Traffic /
Public Spaces –
Knit Upholstery Fabrics

High Traffic / Public Spaces – Knit Upholstery Fabrics

ASTM D4157 (ACT approved #10 Cotton Duck) 30,000 double rubs Wyzenbeek method
ASTM D4966 (12 KPa pressure) 40,000 cycles Martindale method

Disclaimer:

Abrasion test results are not necessarily a reliable indicator of fabric lifespan. Comparative laboratory testing results on the same textiles frequently differ and testing methods do not necessarily correlate well with the variables encountered in actual use by the end-user. Licensees using the ACT performance certification marks and publishing test results exceeding the ACT high-traffic abrasion guideline are required to provide the following statement on their samples, digital media, marketing materials, social media posts, direct and third-party websites:

Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

Notes:

*ACT studies indicate that results of multiple abrasion tests performed on some fabric structures may vary significantly – as much as 60 percent or more. There is no correlation between Wyzenbeek and Martindale results. For more information please refer to abrasion white papers on the ACT website:
<http://www.contracttextiles.org/index.php?page=research>*



**IMPORTANT INFORMATION AND DISCLAIMERS REGARDING ACT'S
VOLUNTARY PERFORMANCE GUIDELINES**

As noted above, ACT's Voluntary Performance Guidelines ("Guidelines") and associated symbols ("Marks") are for information purposes only and are made available to help assist specifiers and end-users in evaluating certain characteristics of contract textiles.

Neither the Guidelines, nor the Marks constitute any promise, representation or warranty that a product or sample that bears or to which a Mark is referenced will in fact comply with applicable federal, state, or municipal laws, codes, rules and regulations concerning the intended use of such product ("Laws"), nor any assurance, representation or guarantee regarding or relating in any manner to the safety of any product or sample that bears or, to which a Mark is referenced.

Whenever appropriate, specifiers and end users should seek the advice of professionals or other knowledgeable persons to ascertain whether a product will in fact comply with applicable Laws.

Understand that the testing and standards ("Standards") referenced in the Guidelines are developed and promulgated by third parties not associated with ACT, and that these Standards often change or are supplemented by such third parties. Accordingly, the fact that a particular Standard is referenced in the Guidelines (and/or associated with any Mark) does not mean, nor is it intended to be a representation that Standard is the most current one.

It is the responsibility of the contract textile vendor and/or the manufacturer (not ACT) to determine in all instances whether or not a textile meets each of the Standards to which a particular Mark is referenced.

THE ASSOCIATION FOR CONTRACT TEXTILES EXPRESSLY DISCLAIMS LIABILITY TO ANY AND ALL PERSONS AND ENTITIES FOR PERSONAL INJURY, PROPERTY DAMAGE, AND ANY OTHER DAMAGE OF ANY KIND OR NATURE, (WHETHER OR NOT SUCH DAMAGES ARE DIRECT, INDIRECT, CONSEQUENTIAL OR COMPENSATORY) RESULTING FROM, OR IN ANY WAY RELATING TO THE GUIDELINES AND MARKS.

The marks  are Registered Certification Marks at the US Patent and Trademark Office and are owned by the Association for Contract Textiles, Inc.